

PRODUCT

Mercury FC 4 mm

ISSUED

NZ-0-05/16



TECHNICAL CHARACTERISTICS

CHARACTERISTIC	TEST METHOD	UNITS	NOMINAL VALUES	TOLERANCES
Visible defects	EN 1850-1	visible	Without defects	
Length	EN 1848-1	m	10,00 -1%	MLV
Width	EN 1848-1	m	1,000 -1%	MLV
Straightness	EN 1848-1	mm	20 mm x 10 m	MLV
Thickness	EN 1849-1	mm	4	±
Watertightness (A)	EN 1928	kPa	60	MLV
External fire performance	EN 13501-5	B roof	F Roof	
Reaction to fire	EN 13501-1	Class	F	Pass
Shear resistance longitudinal / transversal	EN 12317-1	N/50 mm	650 / 450	± 20%
Water vapour transmission proprieties Method A	EN 1931	μ / Sd (m)	120.000 / 480	-20.000
Tensile Strenght Longitudinal / Transversal	EN 12311-1	N/50 mm	750 / 550	± 20%
Elongation at break Longitudinal / Transversal	EN 12311-1	%	45 / 45	- 15 absolut
Resistance to impact	EN 12691	mm	900	MLV
Resistance to static loading Method A	EN 12730	Kg	15	MLV
Resistance to tearing (nail shank)	EN 12310-1	N	180 / 180	- 30%
Dimensional stability Longitudinal / Transversal	EN 1107-1 met. A	%	± 0,3 %	MLV
Flexibility al low temperature	EN 1109	°C	-20	MLV
Flow resistance at elevated temperature	EN 1110	°C	90	MLV
Durability of waterthigness against artificial ageing	EN 1296 / EN 1928	Kpa	60	MLV
Durability of waterthigness against chemicals	EN 1847 / EN 1928	Kpa	60	MLV

FURTHER INFORMATION

Notification code	0120
Certificate number	GB06/69203
Reference norme	EN 13707 / EN 13969
Reinforcement	Non-woven Polyester reinforced with glassfibre
Compound	Bitumen modified with SBS
Surface Finishing	External side: sand, polymeric film PE/PP, non-stick polymeric TNT Internal side: sand, polymeric film PE/PP, non-stick polymeric film TNT
Application method	For internal side sanded, polymeric film, no-stick polymeric TNT: Flame of propane gas / mechanical fixing For internal side sanded: Hot adhesive, cold adhesive (only for EN 13707 norm use, not for EN 13969)
Field of application	Underlayer and intermediate layer Sheet under heavy protection Bitumen damp proof sheets including basement tanking sheets - Product type T For a correct use of the products, please refer to the technical documents issued by the manufacturer. If any law, norm or regulation different from what declared by the manufacturer is in force in the country where the product must be installed, it must be considered as compulsory by the applicator. It is his own responsibility to follow the suitable legislative references.



Legenda:

- 1 - Reinforced bituminous membranes for the roofing waterproofing - Low and middle layers
- 5b - Reinforced bituminous membranes for the roofing waterproofing - Membranes under heavy protection
- 7a - Membranes for stopping the humidity - type A
- 7b - Membranes for stopping the humidity - type T

In terms of the Italian Ministerial Decree n° 65 of 14th March 2003, which sets out 'Classification, labelling and packaging of dangerous preparations in execution of the Directives issued by the Council and by the Commission of the European Community' the product does not contain dangerous elements. In according with the norm EN 13707 (October 2004) the water vapour transmission factor μ can be taken as >20.000. All membranes made by GENERAL MEMBRANE SpA are manufactured by using unblown asphalt and do not contain tar from coal, asbestos, chlorine, used and/or rerefined, are recyclable and are not dangerous waste. The release of a safety data sheet for this product is not compulsory, in any case an informative document is available for the correct use of the product.



www.generalmembrane.it

