

# Resene Blacktop

## driveway coating

Resene Blacktop is a cold applied, heavy-bodied, slip-resistant topping for rejuvenating aged or worn asphalt. Based on a bitumen emulsion with graded fillers that dries to produce a durable, weather and wear resistant finish.

### exterior

### Typical uses

- Asphalt driveways
- Asphalt paths
- Asphalt playgrounds
- Asphalt recreational areas
- Asphalt tennis courts

<b>Vehicle type</b>	Bitumen emulsion
<b>Pigmentation</b>	Inorganic pigments and graded silicas
<b>Solvent</b>	Water
<b>Finish</b>	Matt
<b>Colour</b>	Black, Red, Green
<b>Dry time (minimum)</b>	Dependent upon film thickness Touch: 2 hours Pedestrian use: 6 hours Vehicular use: 48 hours
<b>Recoat time (minimum)</b>	4 hours
<b>Primer required</b>	No
<b>Theoretical coverage</b>	Varies between 0.5-1.0 sq. metres per litre dependent upon surface porosity and profile
<b>Usual no. of coats</b>	1
<b>Abrasion resistance</b>	Good
<b>Durability</b>	Very good
<b>Thinning and clean up</b>	Water when wet; Resene Brush Cleaner when dry
<b>VOC</b>	c. 2-5 grams per litre (see <a href="#">Resene VOC Summary</a> )

### Physical properties

### Recoat time (minimum)

### Primer required

### Theoretical coverage

### Usual no. of coats

### Abrasion resistance

### Durability

### Thinning and clean up

### VOC

### Performance and limitations

#### Performance

1. Easy to apply.
2. Slip-resistant finish.
3. Rejuvenates aged or worn asphalt.
4. Weather and wear resistant finish.
5. An Environmental Choice approved product.

#### Limitations

1. Film may be susceptible to mechanical damage in the early stages of drying.
2. Do not apply at temperatures below 10°C or when it is liable to drop below 10°C during the drying period.
3. Spills of solvent or petrol will result in colour change of Resene Blacktop Green and Red.
4. Due to the nature of Resene Blacktop, batch to batch variations in colour can be expected. Please ensure only one batch number is used, or blend different batches together prior to application.

Please ensure the current Data Sheet and Safety Data Sheet are consulted prior to specification or application of product. If in doubt contact Resene.



# Blacktop driveway coating

## Surface preparation

If moss and mould are present, treat with Resene Moss & Mould Killer (see [Data Sheet D80](#)). Waterblasting is the best surface preparation method prior to coating surfaces.

Remove loose material, dirt, oil and grease. Trim side grass. Repair holes with compatible filling system prior to resurfacing. Consult Resene for advice on resurfacing very old, oxidised asphalt surfaces.

*Sanding dust from old lead or chromate based paints or old building materials containing asbestos may be injurious to the health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.*

## Application

Stir well with a wide flat stirrer before and during application.

Resene Blacktop is best applied with a hi-solids roller. Spread the product evenly over the surface to achieve the recommended coverage. Smooth any ridges immediately. Do not allow roller to become depleted of wet product.

Do not apply if rainfall is likely within the recommended drying period.

If rapid drying is a problem during application, cool the surface by lightly misting with water. Apply coating as soon as the surface water disappears. Avoid painting in the hot sun.

## Precautions

1. A single coat is often sufficient. Faster drying will result from multiple application of thinner coats.
2. Dry times will be longer under cold, damp conditions.

*Please ensure the current Data Sheet is consulted prior to specification or application of Resene products.  
If the surface you propose to coat is not referred to by this Data Sheet, please contact Resene for clarification.*

**In Australia**  
PO Box 785, Ashmore City, Queensland 4214  
Call 1800 738 383, visit [www.resene.com.au](http://www.resene.com.au)  
or email [advice@resene.com.au](mailto:advice@resene.com.au)

**Resene**  
the paint the professionals use

**In New Zealand**  
PO Box 38242, Wellington Mail Centre, Lower Hutt 5045  
Call 0800 RESENE (737 363), visit [www.resene.co.nz](http://www.resene.co.nz)  
or email [advice@resene.co.nz](mailto:advice@resene.co.nz)