

# Resene Wintergrade X-200

low temperature  
curing acrylic  
waterproofing  
membrane

Resene Wintergrade X-200 is designed to cure at very low temperatures down to 2°C. An acrylic waterproofing membrane incorporating the most recent advances in polymer and paint technology, Resene Wintergrade X-200 shows significant advances in the areas of film build, adhesion, penetration, application and durability.

**exterior/interior**

## Typical uses

- Concrete blocks
- Concrete surfaces
- Fibre reinforced cement

<b>Vehicle type</b>	Pure acrylic
<b>Pigmentation</b>	Titanium dioxide/mineral and fibre reinforcement
<b>Solvent</b>	Water
<b>Finish</b>	Eggshell, very fine texture
<b>Colour</b>	White and colours off white.
<b>Dry time (minimum)</b>	Dependent on weather conditions
<b>Recoat time (minimum)</b>	3 hours; recoat when first coat is tough enough to resist the pressure of a firmly pressed, twisted thumb
<b>Primer required</b>	Yes, dependent on surface
<b>Theoretical coverage</b>	First coat: 5 sq. metres per litre Second coat: 7.5 sq. metres per litre
<b>Dry film thickness</b>	2 coats 180 microns
<b>Usual no. of coats</b>	2; blockwork – 3
<b>Abrasion resistance</b>	Very good
<b>Chemical resistance</b>	Very good
<b>Heat resistance</b>	Thermoplastic
<b>Solvent resistance</b>	Good
<b>Durability</b>	Excellent
<b>Thinning and clean up</b>	Do not thin, clean up with water
<b>VOC</b>	c. 10 grams per litre (see <a href="#">Resene VOC Summary</a> )

## Physical properties

## Performance

## Performance and limitations

1. Will cure at very low temperatures.
2. Remarkable ease of application.
3. Superior void and crack filling properties.
4. Excellent durability. Requires no further 'weathering' coats.
5. An Environmental Choice approved product.

## Limitations

1. Apply in temperatures 2°C - 15°C. Application outside this temperature range may affect curing and application properties. Do not apply at temperatures below 2°C or when temperatures are liable to drop below this during the drying period.
2. Old, weathered concrete requires surface conditioning with Resene Sureseal (see [Data Sheet D42](#)).
3. Not designed to be used under ponded water.

Please ensure the current Data Sheet and Safety Data Sheet are consulted prior to specification or application of product. If in doubt contact Resene.



# Wintergrade X-200 acrylic waterproofing membrane

## Surface preparation

### Cracked surfaces

Due to its high film build, Resene Wintergrade X-200 will completely fill cracks up to 1mm. For cracks larger than this, apply one coat of Resene Sureseal (see [Data Sheet D42](#)) before filling the crack with a suitable elastomeric paintable sealant.

### New cementitious surfaces

Clean down thoroughly to remove all dirt, dust and loose material. Ensure surface is free from oil, grease, form release and curing agents. Glossy surfaces require an additional treatment of Resene Concrete Primer (see [Data Sheet D405](#)). Use Resene Limelock (see [Data Sheet D809](#)) on fresh cementitious surfaces to trap any free lime and prevent the appearance of lime staining.

### Old cementitious surfaces

If moss and mould are present, treat with Resene Moss & Mould Killer (see [Data Sheet D80](#)). Waterblasting at 21,000 kps (3000 psi) is the best surface preparation method prior to painting weathered cementitious surfaces. If waterblasting is not possible, remove all loose powdery material by thorough wire brushing. Allow to dry and apply one coat of Resene Sureseal (see [Data Sheet D42](#)).

*Sanding dust from old lead or chromate based paints or old building materials containing asbestos may be injurious to the health if inhaled or ingested. Seek expert advice if the presence of these materials is suspected.*

## Application

### Airless spray

Use a LTX 523 tip or similar. Use a coarse filter in the system as the fibre reinforcement of Resene Wintergrade X-200 may clog finer filters. Apply two coats.

### Brush

Apply two coats at specified rate.

### Roller

Use a 12-20mm synthetic fibre roller or texturing roller depending on surface. Apply two coats.

### Standard spray

Use a De Vilbiss JGA Gun with a D Tip DEX Needle and 107J Air Cap or equivalent.

### Concrete blocks

Due to regional variations in concrete block standards, two coats may be insufficient to waterproof. Waterproofing can only be assured when all voids are filled, therefore three coats over block is a safer specification. Brush or roller application is preferred over block and essential for at least the first coat.

## Precautions

1. Do not thin – thinning destroys build properties.
2. Ensure correct pre-treatment is used and correct surface preparation is undertaken.
3. Use of Resene Wintergrade X-200 in hot conditions will reduce wet edge time and make application difficult.

*Please ensure the current Data Sheet is consulted prior to specification or application of Resene products. If the surface you propose to coat is not referred to by this Data Sheet, please contact Resene for clarification.*

**In Australia**  
PO Box 785, Ashmore City, Queensland 4214  
Call 1800 738 383, visit [www.resene.com.au](http://www.resene.com.au)  
or email [advice@resene.com.au](mailto:advice@resene.com.au)

**Resene**  
the paint the professionals use

**In New Zealand**  
PO Box 38242, Wellington Mail Centre, Lower Hutt 5045  
Call 0800 RESENE (737 363), visit [www.resene.co.nz](http://www.resene.co.nz)  
or email [advice@resene.co.nz](mailto:advice@resene.co.nz)