


Technical Data Sheet



Product Range	Product Name	Dimensional Illustration	Swatch	State	Length (mm)	Width (mm)	Height (mm)	Dimensional Category	Average Weight / Unit (kg)	Core Volume (%)	Units Per m ²	Pack Size	Characteristic Unconfined Compressive Strength (f _{uc}) (MPa)	Cold Water Absorption (%)	Initial Rate of Absorption (IRA) (kg/m ² min)	e'Factor (mm/m)	Durability Class	Liability to Effloresce	Lime Pitting Liability	Solar Absorptance Rating
San Selmo Corso	Arno - Raw			QLD	500	100	40	DW1	3.8	Solid	40.8		>10	<15	1.0-8.0	<1.2	Exposure Grade	Nil to Slight	Nil to Slight	Light
San Selmo Corso	Arno - Textured			QLD	500	100	40	DW1	3.2	Solid	40.8	137	>10	<25	1.0-8.0	<1.2	Exposure Grade	Nil to Slight	Nil to Slight	Light
San Selmo Corso	Brenta - Raw			QLD	500	100	40	DW1	3.8	Solid	40.8		>10	<15	1.0-8.0	<1.2	Exposure Grade	Nil to Slight	Nil to Slight	Light
San Selmo Corso	Livenza - Raw			QLD	500	100	40	DW1	3.8	Solid	40.8		>10	<15	1.0-8.0	<1.2	Exposure Grade	Nil to Slight	Nil to Slight	Medium
San Selmo Corso	Marana - Raw			QLD	500	100	40	DW1	3.8	Solid	40.8		>10	<15	1.0-8.0	<1.2	Exposure Grade	Nil to Slight	Nil to Slight	Dark
San Selmo Corso	Marana - Textured			QLD	500	100	40	DW1	3.2	Solid	40.8	137	>10	<25	1.0-8.0	<1.2	Exposure Grade	Nil to Slight	Nil to Slight	Dark
San Selmo Corso	Piave - Raw			QLD	500	100	40	DW1	3.8	Solid	40.8		>10	<15	1.0-8.0	<1.2	Exposure Grade	Nil to Slight	Nil to Slight	Dark
San Selmo Corso	Piave - Textured			QLD	500	100	40	DW1	3.2	Solid	40.8	137	>10	<25	1.0-8.0	<1.2	Exposure Grade	Nil to Slight	Nil to Slight	Dark
San Selmo Corso	Potenza - Raw			QLD	500	100	40	DW1	3.8	Solid	40.8		>10	<15	1.0-8.0	<1.2	Exposure Grade	Nil to Slight	Nil to Slight	Dark
San Selmo Corso	Potenza - Textured			QLD	500	100	40	DW1	3.2	Solid	40.8	137	>10	<25	1.0-8.0	<1.2	Exposure Grade	Nil to Slight	Nil to Slight	Dark