



ARDEX WPM 5000HD

Self-Adhesive Bituminous Waterproofing Membrane

Self-adhesive SBS waterproofing membrane

Suitable under asphalt

Acts as a barrier to radon and methane gas

Resistance to most chemicals

High tear resistance

High initial tack

Cold applied - perfect for use where flames are not permitted

Self-healing

Quick installation



BRANZ Appraised
Appraisal No.462 [2016]

ARDEX Australia Pty Ltd
20 Powers Road
Seven Hills NSW 2147
Phone: 1300 788 780
technicalservices@ardexaustralia.com
www.ardexaustralia.com

ARDEX New Zealand Ltd
15 Alfred Street
Onehunga, Auckland 1061
Phone: 0800 227 339
info@ardexnz.com
www.ardex.co.nz

ARDEX WPM 5000HD

Self-Adhesive Bituminous Waterproofing Membrane

DESCRIPTION

ARDEX WPM 5000HD is an industrial strength, self-adhesive bituminous membrane. ARDEX WPM 5000HD is reinforced with a layer of polypropylene mesh giving the product exceptionally high mechanical characteristics. ARDEX WPM 5000HD consists of two structural components - SBS modified bitumen with high-tack resins, for easy and versatile installation; and a laminated protection film, providing heat stability and chemical resistance.

USES

ARDEX WPM 5000HD is suitable for below ground tanking parking decks and car parks, trafficable structures, expansion joints, underneath clay tiles or asphalt shingles.

ARDEX WPM 5000HD is ideal for any application where the waterproofing must have high mechanical strength and characteristics.

SUBSTRATES

ARDEX WPM 3000X is suitable for use over concrete, render, screeds, fibre cement sheets, structural or marine grade plywood and polystyrene blocks.

For further substrate types please consult ARDEX Technical Department.

SURFACE PREPARATION

All surfaces must be clean, dry, smooth, free of sharp edges, loose or foreign materials, oil, grease, and other materials that may damage the membrane. If concrete has moisture on the surface use a gas torch to dry and warm before priming.

INSTALLATION

Prior to the installation of ARDEX WPM 5000HD all prepared surfaces must be primed with ARDEX WPM 240 Solvent based primer or ARDEX WPM 247 water based primer.

Starting at the lowest point, the membrane must be installed in accordance with the technical literature. Sheets edges must be overlapped a minimum of 60 mm as marked on the sheets. End laps must be a minimum of 100mm, with upper sheets lapped over lower sheets. Internal and external corners of single layer systems must be reinforced with an extra layer of membrane 300mm wide.

The top edge of ARDEX WPM 3000X must be terminated into a chase or sealed with an ARDEX Pressure Bar and finished with ARDEX Bituminous Sealant.

ARDEX DRS 10 GC protection and drainage membrane must be installed before backfilling in accordance with the product datasheet. Backfilling should commence immediately after the membrane is installed to ensure the membrane is not left exposed to sunlight or UV radiation. In no circumstance should ARDEX WPM 3000X be left exposed to UV for more than 2 months.

Installation of the membrane must be completed by an approved ARDEX installer and who has experience in the application of self-adhesive membranes.

Note: A Licenced Building Practitioner (LBP) is required to carry out Restricted Building Work. An LBP must do or supervise this work. They must work within the scope of their licence class.

ARDEX hydrophilic products should be considered for use in all construction joints depending on the specifics of the installation.

All edges and membrane detailing work must be finished with ARDEX Bituminous Sealant.

If applying asphalt directly over ARDEX WPM 5000HD, the asphalt should be applied as soon as possible after the membrane has been installed. ARDEX recommends applying a minimum 50mm compacted overlay for carpark areas. The topping should be applied at a temperature of between 120-150°C.

STORAGE

ARDEX WPM 5000HD should be stored in a covered area protected against sunlight and UV radiation. Rolls should be stored in a vertical position on a smooth floor so as not to damage the edges.

PACKAGING

ARDEX WPM 5000HD comes in rolls of 20m x 1m x 1.5mm weighing approximately 30kg.

Product Name	Thickness	Colour	Product Code
ARDEX WPM 5000HD	1.5mm	Black	10544

TECHNICAL DATA

CHARACTERISTICS	TEST METHOD	UNITS	NOMINAL VALUE
Tensile Strength Longitudinal Transversal	EN 12311-1	N/50mm n/50mm	925 1005
Elongation Longitudinal Transversal	ASTM D638	% %	32 21
Tear Resistance Longitudinal Transversal	UNI 8202/9	N N	350 300
Adhesion to primed concrete	ASTM D1000	N/mm	4.9
Adhesion to steel	ASTM D1000	N/mm	5.8
Puncture resistance	ASTM E154	N/65mm	220
Vapour transmission rate	ASTM E969	g/m/24hrs	0.3
Cold flexibility	ASTM D146	°C	-30
Softening point		°C	110
Maximum temperature resistance		°C	150

**Toll Free Technical Services:
1800 224 070 (Australia)
0800 227 339 (New Zealand)**

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable New Zealand & Australian Standards, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX New Zealand Ltd 2018.

All aforementioned products are the trademarks of ARDEX New Zealand Ltd, its licensors and affiliates. This data sheet was issued in October 2018 and is valid for 3 years, in some instances a newer version may be published. Always refer to www.ardex.co.nz for the latest technical data from ARDEX New Zealand Ltd.