



2 IN 1 PRIMER AND MOISTURE BARRIER IN ONE SYSTEM

Okatmos® DSG

Dispersion based moisture barrier primer

- for absorbent and non-absorbent substrates
- quick-drying
- solvent-free and very low emissions
- sanitising characteristics
- high bond strength
- interior use
- as a moisture barrier against increased humidity in unheated cementitious substrates
- protection of the calcium sulphate screed against moisture



PRODUCT DESCRIPTIONS

Solvent-free, sanitizing moisture barrier and primer with high bond strength for well prepared substrate. For absorbent and non-absorbent substrates to use before levelling, sealing, thin-bed tile installation or the installation of textile/flexible floor surfaces and parquet/engineered wood flooring.

Okatmos® DSG can be used as moisture controlled dispersion primer on cementitious substrates such as cement screeds or concrete barrier against excessive moisture.

- Residual moisture of up to 3 CM-% (85 % RMC) for unheated cement screed (2-layer application) and 4 CM-% (90 % RMC) (3-layer application).
- For unheated concrete substrates (also under cement composite screed) with a maximum residual moisture of 4.5 by weight-% (90 % RMC) (2 layers) and 6 by weight-% (95 % RMC) (3 layers) according to DARR method measurements.
- For use under large ceramic tiles to provide moisture barrier from self-levelling compounds or normal-set thin-bed mortars.
- No thickness limitation when using Kiesel self-levelling compounds over 2-layerd applications on calcium sulphate screeds.

Okatmos® DSG is also a suitable primer for smooth, dense and non-absorbent substrates such as, e.g. old tile, natural stone or artificial stone surfaces before levelling work or thin-bed tile installations. Not suitable over sulphite liquid adhesives, magnesia based screeds and stonewood-screeds.

Sanitising properties provide an additional odour containing properties.

Okatmos® DSG does not replace necessary or required waterproofing membranes.

SUBSTRATE PREPARATION

The substrate must be dry, clean and sound. Remove mechanically any bitumen/oil based or loose products. The existing substrates must also comply with the applicable local and national standards and regulations in each case. The respective substrate must be tested in accordance with the applicable standards and when in doubt contact Kiesel technical department.

PROCESSING

Okatmos® DSG is to be applied undiluted to non-absorbent substrates with the use of a lamb's wool roller, a brush or ordinary paint roller providing proper transfer. **Okatmos® DSG** is always diluted at a ratio of 1:1 for the first application on absorbent substrates. A second and third coat should be applied when first coat is fully dry. Coverage is approx. 120–130 g/m² for undiluted application and approx. 60–70 g/m² for diluted application.

Allow the primer to dry thoroughly after applying. Use a Kiesel pre-coating roller and apply a full and even coat of **Okatmos® DSG** to the substrate, filling any pores. Avoid pooling.

TOOL

Brush, lamb's wool roller
Kiesel pre-coating roller if used to provide a barrier against moisture (article no. 15029, EAN code 4015705120291).

CLEANING

Clean tools immediately with water.

COVERAGE

approx. 150 g/m² on non-absorbent substrates
 approx. 60–70 g/m² when diluted with water at a ratio of 1:1
 approx. 120–130 g/m² when used undiluted

SPECIFICATIONS

Color	red
Application	interior, on walls and floors
Application temperature	> 10 °C (substrate)
Drying time*	approx. 0.5 – 2 hours minimum 0.5 – 1 hour diluted and at least 1 hour if undiluted (last application, at least 2 hours and after drying)
Floor heating system	suitable
GISCODE	D 1 according to the Technical Rules for Hazardous Materials (TRGS) 610
EMICODE	EC 1Plus according to the GEV
Shelf life	store in frost protected area for up to 12 months

* At +20°C and 65% relative humidity. Higher temperatures will reduce and lower temperatures will extend these values accordingly.

PACKAGING

Packaging	Item no.	EAN
60x 10 kg plastic canister	49077	4015705490779

The aforementioned information, especially the proposals for processing and utilizing our product, is based on our knowledge and experience. We recommend that you carry out your own tests in every case to ensure the suitability of our products for the intended process and processing purposes because of the different materials and the working conditions which lie beyond our area of influence. No liability can be derived from this advice or from verbal advice, unless we are responsible for (criminal) intent or gross negligence in this respect.

