

# Resene ArmourCat 810

## metallic effects

Resene ArmourCat 810 is a two pack, acid-catalysed finish formulated to produce metallic and special effects. May be overcoated with either Resene ArmourCat or DuraGloss clear finishes for enhanced wear and appearance.

## interior

## Typical uses

- Desks
- Doors
- Furniture
- Kitchen units
- Shop fittings
- Timber fixtures
- Wall units/shelving

## Physical properties

<b>Vehicle type</b>	Acid-catalysed alkyd urea resin system
<b>Hardener</b>	Organic acid
<b>Pigmentation</b>	Metallic/special effect/organic/inorganic
<b>Solvent</b>	Aromatic/alcohol
<b>Finish</b>	Aluminium: Semi-gloss Blast grey: Satin
<b>Colour</b>	A range of metallic effects from the Resene Metallics and Special Effects colour chart
<b>Pot life</b>	8 hours at 18°C
<b>Mix ratio</b>	10 parts base: 1 part hardener (by volume)
<b>Induction time</b>	5-15 minutes
<b>Dry time (minimum)</b>	Tack free: 10-15 minutes at 18°C To handle: 2 hours at 18°C Full cure: 7 days at 18°C
<b>Recoat time (minimum)</b>	Resene ArmourCat Clear: 2 hours at 18°C Resene ArmourCat Clear: Maximum: 7 days at 18°C DuraGloss Clear: Minimum: 6 hours at 18°C DuraGloss Clear: Maximum: 7 days at 18°C
<b>Sealer/undercoat reqd</b>	Yes, Resene ArmourCat 805 (new MDF/wood)
<b>Theoretical coverage</b>	10 sq. metres per litre.
<b>Volume solids</b>	Aluminium: 40% (mixed, unthinned) Blast grey: 46% (mixed, unthinned)
<b>Thinning and clean up</b>	Resene Thinner No.16
<b>Overcoating</b>	Resene ArmourCat 842 (see <a href="#">Data Sheet RA89</a> ), Resene ArmourCat 843 (see <a href="#">Data Sheet RA90</a> ) and DuraGloss Clear Satin/Gloss
<b>Pack size</b>	1 and 4 litre

## Performance

## Performance and limitations

1. Quick drying.
2. Ability to match metallic effects between walls and furniture.
3. In environments where maximum chemical, solvent or abrasion resistance is required the use of a DuraGloss Clear finish as a protective clear coat is recommended.

## Limitations

1. Dry and recoat times are affected by low temperatures and high humidities.
2. Interior use only.
3. Spray application only.

# ArmourCat 810 metallic effects

## Surface preparation

### New MDF board, timber

Prime bare substrate with Resene ArmourCat 805 sealer/undercoat (see [Data Sheet RA84](#)).

Dry sand cured primer with 320 grit sandpaper to achieve a smooth even finish. Ensure the sanded substrate is free from dirt, dust, loose material, oil and grease.

### Repaint

All surfaces must be clean, sound, free from dust, chalking, flaking paint, dirt, mould or grease.

Sand entire surface to a smooth finish. Feather back damaged coatings to a sound edge, spot prime bare areas with Resene ArmourCat 805 (see [Data Sheet RA84](#)). Allow to cure for minimum recoat time then apply a full coat of Resene ArmourCat 805 (see [Data Sheet RA84](#)) to all areas. A test patch should be done to check adhesion and that the Resene ArmourCat 805 (see [Data Sheet RA84](#)) does not lift the existing paint.

**Not suitable for repaints of existing nitro cellulose or two pack urethane based furniture coating systems.**

## Application

### Mixing

Thoroughly stir contents of the base container until uniform using an explosion proof mixer.

Add one part of Resene ArmourCat Series hardener to ten parts of Resene ArmourCat 810 base and power mix until uniformly blended. Allow mixed product to stand for 5-15 minutes before use or thinning.

### Thinning

Thin up to 10% by volume of mixed material with Resene Thinner No.16. The quantity of thinner required will vary according to spray equipment and environmental conditions. Avoid excessive thinning as heavy settling of metallic pigments may occur resulting in an uneven finish.

### Application

Spray only (conventional or pressure pot). Consult your Resene Automotive Technical Representative for assistance with spray set-up and application techniques before commencing work.

## Safety precautions

Consult Safety Data Sheet for this product prior to use. Users should ensure that they are familiar with all aspects concerning safe application of this product. **IF IN DOUBT, DO NOT USE THIS PRODUCT.**

*Please ensure the current Data Sheet is consulted prior to specification or application of Resene products.  
If the surface you propose to coat is not referred to by this Data Sheet, please contact Resene for clarification.*

**In Australia**  
PO Box 785, Ashmore City, Queensland 4214  
Call 1800 738 383, visit [www.resene.com.au](http://www.resene.com.au)  
or email [advice@resene.com.au](mailto:advice@resene.com.au)

**Resene**  
the paint the professionals use

**In New Zealand**  
PO Box 38242, Wellington Mail Centre, Lower Hutt 5045  
Call 0800 RESENE (737 363), visit [www.resene.co.nz](http://www.resene.co.nz)  
or email [advice@resene.co.nz](mailto:advice@resene.co.nz)

Printed on environmentally responsible paper, which complies with the requirements of environmental management systems EMAS and ISO14001. Please recycle.