



Application: Flexible sheets for water proofing –
Part 1: Underlays for discontinuous roofing
EN 13859-1

Application: Flexible sheets for water proofing –
Part 2: Underlays for walls
EN 13859-2

Style name
Type of carrier

2506B
HDPE and PP composite (with or without integrated tape)

Language **English**

PROPERTY	METHOD	UNITS	NOMINAL	MINIMUM	MAXIMUM
FUNCTIONALITY: WATER VAPOUR TRANSMISSION, WATER TIGHTNESS, WEATHER DURABILITY, FIRE CLASS					
Water vapour transmission (sd)	EN ISO 12572 (C)	m	0,03	0,015	0,045
Temperature resistance	-	°C	-	-40	+100
Flexibility at low temperature	EN 1109	°C	-	-	-40
UV exposure	-	months	-	-	4
Product- / Functional layer thickness	-	µm	420 / 220	-	-
Water tightness	EN 1928 (A)	class	W1	-	-
Water column	EN 20811	m	-	2	-
Reaction to fire	EN ISO 11925-2	class	E	-	-
PHYSICAL AND MECHANICAL PROPERTIES					
Mass per unit area	EN 1849-2	g/m ²	148	138	158
Maximum tensile force (MD)	EN 12311-1	N/50mm	345	290	400
Elongation at max. tensile force (MD)	EN 12311-1	%	14	10	18
Maximum tensile force (XD)	EN 12311-1	N/50mm	290	235	345
Elongation at max. tensile force (XD)	EN 12311-1	%	20	15	25
Resistance to tearing MD (nail shank)	EN 12310-1	N	175	125	225
Resistance to tearing XD (nail shank)	EN 12310-1	N	175	125	225
PROPERTIES AFTER AGEING					
Artificial ageing by UV and heat:	EN 1297 & EN 1296	residual value			
Water tightness	EN 1928 (A)	class	W1	-	-
Maximum tensile force (MD)	EN 12311-1	%	90	-	-
MD elongation at max. tensile force	EN 12311-1	%	85	-	-
Maximum tensile force (XD)	EN 12311-1	%	90	-	-
XD elongation at max. tensile force	EN 12311-1	%	85	-	-
ADDITIONAL PROPERTIES					
Length (customer related, expressed in m)	EN 1848-2	deviation in %	0	0	-
Width (customer related, expressed in mm)	EN 1848-2	deviation in %	0	-0,5	+1,5
Straightness	EN 1848-2	mm/10m	-	-	30
Dimensional stability (MD & XD)	EN 1107-2	%	-	-	1
Water tightness of seams	EN 13859-1	pass / no pass	pass	-	-
Resistance to penetration of air	EN 12114	m ³ /(m ² h 50Pa)	-	-	0,1
Windtight	-	-	yes	-	-

Effective date: 29/09/2014

First CE: 23/11/2005

DuPont de Nemours (Luxembourg) S.à r.l.
Rue General Patton, L-2984 Luxembourg

Tel +352 3666 5885
Fax +352 3666 5021
tyvek.info@lux.dupont.com
www.construction.tyvek.com

Some test methods are modified according to the EN 13859-1:2014 & EN 13859-2:2014 and/or according to the DuPont ISO 9001:2008 certified quality system (for details please contact your regional DuPont representative). All values are based on roll average. This information corresponds to our current knowledge on the subject. It is offered in accordance with REGULATION (EU) No 305/2011 OF THE EUROPEAN PARLIAMENT AND OF THE COUNCIL of 9 March 2011 laying down harmonised conditions for the marketing of construction products and repealing Council Directive 89/106/EEC. It is not intended to substitute for any testing you may need to conduct to determine for yourself the suitability of our products for any application other than the application as specified herein. This information may be subject to revision as new knowledge and experience becomes available. Since we cannot anticipate all variations in actual end-use conditions, DuPont makes no warranties and assumes no liabilities in connection with any use of this information for applications other than the application as specified herein. Nothing in this publication is to be considered as a license to operate under or a recommendation to infringe any patent right. Product safety information is available on request. This data sheet is a printed document and is valid without signature.

the
Original
proven since 1990



Tyvek.