

Dulux Professional Ultra 5 Surfacers, Prep & Finish

NZDD1416

Part A	664-97583
---------------	-----------

Description

Previously known as DULUX PROFESSIONAL Ultra 5 Surfacers, Prep & Finish
 DULUX PROFESSIONAL Ultra 5 Surfacers, Prep & Finish is a 100% acrylic low VOC surface preparation specially designed to be an important component in achieving a Level 5 finish on new or pre-painted interior plasterboard surfaces.

Features

- Aid to achieve a Level 5 finish
- High film build
- Versatile
- Water based
- Sands easily
- Consistent coverage

Benefits




- Minimises problems of porosity difference between joints and substrate.
- Achieves high film build without running or sagging.
- May be tinted to light colours for use as a ceiling finish coat in dry areas.
- Easy clean up, low odour.
- Gives a better, smoother finish with less effort.
- Hides minor surface imperfections and promotes improved paint flow.

Uses

Use DULUX PROFESSIONAL Ultra 5 Surfacers, Prep & Finish where a good quality, professional finish is required. This product is suitable for use on paperfaced plasterboard, interior concrete, fibre cement sheet, solid plaster and pre-painted areas.

Performance Guide

Weather	Not recommended for exterior use.	Heat Resistance	Up to 70°C.
Water	Excellent when topcoated with approved topcoat.	Solvent	Sensitive to aromatic hydrocarbons, alcohols and ketones.
Abrasion	Good when topcoated.		

Typical Properties																											
Thinner	Thinning is not recommended.	Colour	White.																								
Components	1	Number Of Coats	1																								
Toxicity	Lead free. Dry film is non-toxic.	V.O.C. Level	3 g/L																								
Touch Dry	2 Hours																										
Clean Up	 Water																										
Clean Up Description	Clean all equipment with water.																										
Application Method	 Air Spray  Airless Spray																										
Application Conditions	<table border="0" style="width: 100%;"> <tr> <td style="text-align: center;">Solids By Volume</td> <td style="text-align: center;">40</td> <td></td> <td></td> </tr> <tr> <td></td> <td style="text-align: center;">Min</td> <td style="text-align: center;">Max</td> <td style="text-align: center;">Recommended</td> </tr> <tr> <td>Wet Film Per Coat (microns)</td> <td style="text-align: center;">338</td> <td style="text-align: center;">338</td> <td style="text-align: center;">338</td> </tr> <tr> <td>Dry Film Per Coat (microns)</td> <td style="text-align: center;">135</td> <td style="text-align: center;">135</td> <td style="text-align: center;">135</td> </tr> <tr> <td>Recoat Time (min)</td> <td style="text-align: center;">4 Hours</td> <td style="text-align: center;">Indefinite</td> <td></td> </tr> <tr> <td>Theoretical Spread Rate (m²/L)</td> <td style="text-align: center;">3</td> <td style="text-align: center;">3</td> <td style="text-align: center;">3</td> </tr> </table>			Solids By Volume	40				Min	Max	Recommended	Wet Film Per Coat (microns)	338	338	338	Dry Film Per Coat (microns)	135	135	135	Recoat Time (min)	4 Hours	Indefinite		Theoretical Spread Rate (m ² /L)	3	3	3
Solids By Volume	40																										
	Min	Max	Recommended																								
Wet Film Per Coat (microns)	338	338	338																								
Dry Film Per Coat (microns)	135	135	135																								
Recoat Time (min)	4 Hours	Indefinite																									
Theoretical Spread Rate (m ² /L)	3	3	3																								

Application Guide	
Surface Preparation	<ul style="list-style-type: none"> All surfaces must be thoroughly clean and free of all loose dirt, grease, mould, mildew and wax, surface chalk and loose or flaking paint, efflorescence and loose surface plaster. Sand smooth and dust down. Prepare surface in accordance with the requirements of the chosen system.
Application Procedure And Equipment	<ul style="list-style-type: none"> Conventional or airless spray. Stir contents thoroughly before and during use. Apply direct from the can. May be applied to dampened surfaces. <p>Airless Spray: Should be applied using a "cross-hatch" method to produce a film build of 150 to 200 microns. This involves holding the gun approximately 600mm from the wall and spraying an even coat horizontally across the substrate with a 50% overlap. Spraying on the next coat vertically completes application.</p> <p>An airless sprayer capable of applying 3.0 litres per minute at the pressure of 3300psi through a 21 to 27 thou tip with a 3/8 inch hose fitting should be used. Similar to the Graco 695 model. A 60 mesh in-line filter can be used. DO NOT USE FINE PAINT FILTERS.</p> <p>Sanding: Sand to a smooth surface free of any sign of peel or texture with 180 to 220 grit sandpaper.</p>

Health And Safety			
MSDS Number	0	Using Safety Precautions	For detailed information refer to the product label and the current Material Safety Data Sheet available through Dulux Sales and Customer Service offices.
Health Effects	Splashes to the eye may cause eye irritation. When spraying, inhalation of mists may produce respiratory irritation.	Protective Equipment	Wear eye protection and when spraying wear a suitable mask.
Disposal	Do not contaminate stormwater with product or product washings. Do not pour product down the drain. Unwanted product should be brushed out on newspaper, allowed to dry and then disposed of via domestic waste collection. Empty containers should be left open in a well ventilated area to dry out. When dry, recycle the container via recycling programmes. Disposal of empty paint containers via recycling programmes may differ between local authorities. Check with your local council first. Dulux recommends the use of the ENVIROWASH system for treating washings from water based paints.		
In the case of emergency, please call 0800 734 607			

Precautions And Limitations

Do not apply if temperature is under 10°C, or when temperature of surface may fall below 10°C during the drying period, otherwise film formation will not be complete and a fall-off in properties will result.
 For all walls and when product is used in bathrooms and other wet areas DULUX PROFESSIONAL Ultra 5 Surfacer, Prep & Finish must be top-coated with the appropriate DULUX finish coat.
 Where accurate colour reproduction is required DULUX PROFESSIONAL Ultra 5 Surfacer, Prep & Finish must be top-coated with the appropriate DULUX finish coat.
 When coating paper-faced wallboard that has aged and yellowed DULUX recommends that the surface be sealed with DULUX Precoat Sealer Binder.
 For fibrous plaster surfaces DULUX recommends that the surface be sealed with DULUX Precoat Sealer Binder.
 As with all higher build water borne coatings, best drying is obtained when there is a reasonable airflow over the coated surface.

Transport And Storage

Pack A	664-97583	Shipment Name	Not dangerous goods.; No special transport requirements.
Size 10 Litre		Weight 16.1 kg	
Flash Point	NA	UN Number	NA
Dangerous Goods Class	NA	Package Group	NA

Disclaimer

Dulux and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating systems.
 DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (New Zealand) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "Orica" "Dulux" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "Acratex" and Other marks followed by ® are registered trademarks. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road NZ ACN 133 404 118