

## Dulux AcraTex 958 AcraSand

**NZDA0990**



<b>Part A</b>	194-51943
---------------	-----------

<b>Product Overview</b>
DULUX AcraTex 958 AcraSand is an extremely tough 100% pure acrylic high build coating, especially formulated to produce a granular, near flat, appearance very much like that of fine granular sandstone in two coats..

<b>Features And Benefits</b>	
<ul style="list-style-type: none"> <li>Water based</li> <li>Easy to texture</li> <li>Versatile application</li> <li>10 year warranty</li> </ul>	<ul style="list-style-type: none"> <li>Easy, safe and economical clean-up.</li> <li>Range of texture profiles possible.</li> <li>Quick, efficient application with roller, spray and trowel.</li> <li>Guaranteed long term exterior durability.</li> </ul>

<b>Uses And Typical Specifications</b>	
<b>Uses</b>	DULUX AcraTex 958 AcraSand can be used where extreme high performance is required and where a more natural granular appearance is aesthetically desired. Its mid build rheology will cover small holes and fine hairline cracks in a single fast applying and economical coat on all masonry substrates. It should be overcoated with DULUX AcraTex AcraShield Advance to give true colour consistency

<b>Performance Guide</b>			
<b>Weather</b>	Excellent resistance to cracking, flaking and chalking as part of full system.	<b>Salt</b>	Resists salt spray especially when topcoated with DULUX AcraTex AcraShield Advance
<b>Heat Resistance</b>	Up to 90C (dry).	<b>Solvent</b>	Resists alcohol and aliphatic hydrocarbons. Sensitive to strong solvents.
<b>Abrasion</b>	Good abrasion resistance especially when topcoated with DULUX AcraTex AcraShield Advance		

<b>Typical Properties</b>																											
<b>V.O.C Content</b>	<75 g/L	<b>Clean Up</b>	Clean up water. Clean all equipment in water.																								
<b>Application Method</b>	 Brush  Roller																										
<b>Application Conditions</b>	<table border="1"> <tr> <td><b>Solids By Volume</b></td> <td>50</td> <td></td> <td></td> </tr> <tr> <td></td> <td><b>Min</b></td> <td><b>Max</b></td> <td><b>Recommended</b></td> </tr> <tr> <td><b>Wet Film Per Coat (microns)</b></td> <td>250</td> <td>330</td> <td>250</td> </tr> <tr> <td><b>Dry Film Per Coat (microns)</b></td> <td>125</td> <td>165</td> <td>125</td> </tr> <tr> <td><b>Recoat Time (min)</b></td> <td>24 hours</td> <td>Indefinite</td> <td></td> </tr> <tr> <td><b>Theoretical Spread Rate (m<sup>2</sup>/L)</b></td> <td>4</td> <td>3.03</td> <td>4</td> </tr> </table>	<b>Solids By Volume</b>	50				<b>Min</b>	<b>Max</b>	<b>Recommended</b>	<b>Wet Film Per Coat (microns)</b>	250	330	250	<b>Dry Film Per Coat (microns)</b>	125	165	125	<b>Recoat Time (min)</b>	24 hours	Indefinite		<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>	4	3.03	4		
<b>Solids By Volume</b>	50																										
	<b>Min</b>	<b>Max</b>	<b>Recommended</b>																								
<b>Wet Film Per Coat (microns)</b>	250	330	250																								
<b>Dry Film Per Coat (microns)</b>	125	165	125																								
<b>Recoat Time (min)</b>	24 hours	Indefinite																									
<b>Theoretical Spread Rate (m<sup>2</sup>/L)</b>	4	3.03	4																								

<b>Application Guide</b>	
<b>Surface Preparation</b>	<ul style="list-style-type: none"> <li>All surfaces must be cured, clean, sound and free of all contaminants such as form oils, release agents and mortar splashes. Surface imperfections, misalignments and protrusions must be levelled, patched and completely flush to surrounding surfaces. Metal tie wires, etc on surface must be removed and treated against corrosion. Prime substrate with DULUX AcraPrimer 501/8 HAR Primer or surfaces of powdery nature will require consolidation with DULUX AcraTex AcraPrime 501/2. If using DULUX AcraPrime 501/8 HAR primer, ensure alkaline surfaces have aged (a minimum of 7 days curing, possibly longer depending on conditions). If using a different primer ensure alkaline surfaces have aged for 28 days minimum.</li> </ul>
<b>Application Procedure And Equipment</b>	<ul style="list-style-type: none"> <li>Brush and roller</li> <li>Refer to the Dulux AcraTex Applicators Training Manual for detailed instructions.</li> <li>A minimum of two coats is required (minimum DFT of 125 micrometres) to avoid "holidays" in the coating.</li> </ul>

Health And Safety			
<b>MSDS Number</b>	14557369	<b>Using Safety Precautions</b>	For detailed information refer to the current Material Safety Data sheet available through Dulux NZ Sales and Customer Service Offices.
<b>MSDS Link</b>	<a href="http://msds.duluxgroup.com/pdf/shess-en-cds-020-000014557369.pdf">http://msds.duluxgroup.com/pdf/shess-en-cds-020-000014557369.pdf</a>		
<b>Health Effects</b>	Splashes to the eye may cause eye irritation. When spraying, inhalation of mists may produce respiratory irritation.	<b>Protective Equipment</b>	Wear eye protection and when spraying wear a suitable mask.
<b>Disposal</b>	Do not contaminate stormwater with product or product washings. Do not pour product down the drain. Unwanted product should be brushed out on newspaper, allowed to dry and then disposed of via domestic waste collection. Empty containers should be left open in a well ventilated area to dry out. When dry, recycle the container via recycling programmes. Disposal of empty paint containers via recycling programmes may differ between local authorities. Check with your local council first.		
<b>In the case of emergency, please call 0800 734 607</b>			

Precautions And Limitations
<p>A DULUX warranty will be provided confirming protection against flaking &amp; peeling for a period of seven years when the full DULUX AcraTex system is applied by a DULUX trained applicator, according to specification, &amp; at the specified spreading rates, &amp; to the surface preparation details described in the AcraTex Specification Manual.</p> <p>DULUX AcraTex Acra-Sand must only be applied in air temperatures between 10C and 30C and must be protected from rain and frost for the first 24 hours. Avoid application in full sun or hot, windy conditions.</p>

Transport And Storage			
<b>Pack A</b>	194-51943	<b>Shipment Name</b>	Not dangerous goods.No special transport requirements.
<b>Size</b>	15 litre	<b>Weight</b>	23 kg
<b>Flash Point</b>	NA	<b>UN Number</b>	NA
<b>Dangerous Goods Class</b>	NA	<b>Package Group</b>	NA

**Disclaimer**

Dulux, Selleys and Other marks followed by ® are registered trademarks. Marks followed by the symbol of ™ are trademarks.

The data provided within the Duspec system is correct at the time of publication, however it is the responsibility of those using this information to check that it is current prior to specifying or using any of these coating/product systems.

DISCLAIMER: Any advice, recommendation, information, assistance or service provided by any of the divisions of DuluxGroup (New Zealand) Pty Ltd or its related entities (collectively, DuluxGroup) in relation to goods manufactured by it or their use and application is given in good faith and is believed by DuluxGroup to be appropriate and reliable. However, any advice, recommendation, information, assistance or service provided by DuluxGroup is provided without liability or responsibility PROVIDED THAT the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon DuluxGroup by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Coating/product systems can be expected to perform as indicated on the Duspec Spec Sheet so long as applications and application procedures of the individual products are followed as recommended on the appropriate Product data Sheet. "DuluxGroup" "Dulux" "Selleys" "Berger" "Berger Gold Label" "Hadrian" "Walpamur" "Levene" "AcraTex" and Other marks followed by ® are registered trademarks. Marks followed by the symbol ™ are trademarks.

Please note that this document is only valid for 60 days from the date of issue.

DuluxGroup (New Zealand) Pty Ltd 150 Hutt Park Road NZ ACN 133 404 118