

Technical data sheet
Membrane mdm[®] Ventia Iron Black Self Adhesive

Characteristic	Test method	Unit	Result	Tolerance	
				Min.	Max.
Length	EN 1848 -2	m	50	0	+0,5
Width	EN 1848 -2	m	1,5	-0,005	+0,005
Straightness	EN 1848 -2	-	Pass	-	-
Mass per unit area	EN 1849 -2	g/m ²	130+50	-10%	10%
Thickness	EN 1849 -2	mm	0,6	-0,15	+0,2
Reaction to fire	AS 1530.2-1993	class	< 5	-	-
Resistance to water penetration	EN 1928 A	class	W1	-	-
Water vapour transmission Properties, Sd [m]	EN ISO 12572 C	m	0,090	-0,03	+0,16
Resistance to penetration of air	EN 12114	m ³ /(m ² x h x 50 Pa)	Max 0,05	-	-
Tensile properties: Maximum tensile force	EN 12311-1	N/50mm	MD 280	-80	+80
			CD 190	-60	+60
Tensile properties: elongation	EN 12311-1	%	MD 70	-45	+45
			CD 110	-55	+55
Resistance to tearing (nail shank)	EN 12310-1	N	MD 135	-45	+45
			CD 170	-60	+70
Dimensional Stability	EN 1107-2	%	2	-	-
Stability at low temperature	EN 1109	°C	-40	-	-
Artificial ageing by long term exposure to the combination Of UV radiation and elevated Temperature and heat (80°C)	Elongation EN 13859-1 annex C	%	MD 50	-25	+25
			CD 50	-30	+30
	Tensile strength EN 13859-1 annex C	N/50mm	MD 250	-55	+55
			CD 160	-35	+35
	Resistance to water penetration EN 13859-1 annex C	class	W1	-	-

 Bielsko-Biała, 20.12.2024
 (Data i miejsce wystawienia)

 VAT No. PL5482614481
 Registered in Poland, KRS No. 0000354101
 Share capital: 992 500 PLN

 Bank Handlowy w Warszawie S.A., SWIFT: CITIPLPX
 IBAN: PL 67 1030 1508 0000 0008 1613 6008 (PLN)
 IBAN: PL 23 1030 1508 0000 0008 1613 6024 (EUR)
 IBAN: PL 98 1030 1508 0000 0008 1613 6032 (USD)